

PRODUCT DATA SHEET


supercapSBS[®] SC100WWH

USAGE: Cap APPLICATION: Cold Adhesive / Hot Asphalt



ASTM-D-6163-00^{e1} Grade G
Tested in Accordance with ASTM-D-5147

1 ENERGY STAR[®] (Version 2)
2 CRRC Title 24 If $\epsilon > 0.75$ Reflect = 0.70 min
3 CRRC Title 24 If $\epsilon < 0.75$ Reflect = 0.70 + 0.34 * (0.75 - $\epsilon_{initial}$)



Dimensions and Mass	Unit	ASTM Minimum			MBTechnology Nominal
		Type 1	Type 2	Type 3	
Reinforcement		High Tensile Strength Fiber Glass Scrim Mat (Asbestos-Free)			
Area	ft ²	109.7 Actual / 100 Coverage (excluding selvage)			
Roll Weight	lbs	-	-	-	100
Roll Length	feet + inches	-	-	-	33' 4"
Roll Width	inches	-	-	-	39.50
Selvage Width	inches	3	3	3	3.50
Thickness (Over All)	mil	95	105	120	131
Thickness (Selvage)	mil	-	-	-	99
Net Mass	lbs/100ft ²	65	75	75	91.1
Bottom Coating Thickness Heat Welding Applications	mil	N/A	N/A	N/A	35

Physical Properties	Unit	ASTM Minimum			MBTechnology Nominal	
		Type 1	Type 2	Type 3		
Tensile Strength	lbs/in	30	80	150	MD	119
Max Load at 73.4°F (23°C):					CD	105
Tensile Strength (After Heat Cond)	lbs/in	30	80	150	MD	TBD
Max Load at 73.4°F (23°C):					CD	TBD
Tensile Strength	lbs/in	70	150	180	MD	TBD
Max Load at 0°F (-18°C):					CD	TBD
Tensile Strength (After Heat Cond)	lbs/in	70	150	180	MD	TBD
Max Load at 0°F (-18°C):					CD	TBD
Elongation at Max Load	%	2	4	3	MD	4
73.4°F (23°C):					CD	4
Elongation at Max Load (After Heat Cond)	%	2	4	3	MD	TBD
73.4°F (23°C):					CD	TBD
Elongation at Max Load	%	1	2	2	MD	TBD
0°F (-18°C):					CD	TBD
Elongation at Max Load (After Heat Cond)	%	1	2	2	MD	TBD
0°F (-18°C):					CD	TBD
Ultimate Elongation	%	3	40	2	MD	6
73.4°F (23°C):					CD	19
Ultimate Elongation (After Heat Cond)	%	3	20	2	MD	TBD
73.4°F (23°C):					CD	TBD
Tear Strength	lbs	35	110	210	MD	137
73.4°F (23°C):					CD	171
Low Temperature Flexibility (As Mfg) :	maximum	-18°C (0°F)	-18°C (0°F)	-15°C (5°F)	MD & CD	-5°C (23°F)
Low Temperature Flexibility (After Heat Cond) :	maximum	-18°C (0°F)	-18°C (0°F)	-15°C (5°F)	MD & CD	TBD
Dimensional Stability:	% (max)	0.5	0.5	0.5	MD & CD	< 0.20
Compound Stability:	°C	102	102	91		102
Granule Embedment:	grams	2 max	2 max	2 max		< 1.0
Reflectance (Initial) C-1549:	≥ 0.65 ¹	≥ 0.70 ²	≥ TBD ³			TBD
Reflectance (3 Year Aged) C-1549 or E1918:	≥ 0.50 ¹	≥ TBD ²	≥ TBD ³			TBD
Thermal Emittance (Initial) C-1371:	Report ¹	≥ 0.75 ²	≤ 0.75 ³			TBD
Thermal Emittance (3 Year Aged) C-1371:	Report ¹	TBD ²	TBD ³			TBD

Ultimate Elongation is reported at point where load has dropped down to 5% of its original max.



MBTECHNOLOGY
 SUPERIOR ROOFING & UNDERLAYMENT SYSTEMS
 188 S. Teilman Avenue • Fresno, California 93706-1334 U.S.A. • Toll Free: 800-621-9281 • Fax: 559-233-4607
 www.mbtechnology.com

THE
DIFFERENCE
IS
QUALITY