

PRODUCT DATA SHEET

fastorchSBS® FT120GSA

Membrane For Roofing Systems
As To An External Fire Exposure Only - 51P6



Subject to the conditions of Approval as a roof cover when installed as described in RoofNav.



USAGE: Interply

APPLICATION: Torch

Florida State Approved



	Unit	Minimum Values As Required by ASTM-D-6163			MBTechnology	
		Type 1	Type 2	Type 3	Nominal	
Reinforcement		Fiberglass Mat (Asbestos Free)				
Roll Coverage		1 Square				
Roll Weight	lbs	-	-	-	88	
Roll Length	feet + inches	-	-	-	33' 4"	
Roll Width	inches	-	-	-	39.75	
Thickness (Over All)	mil	80	80	80	116	
Lap Lines (From Each Side)	inches	3	3	3	3.75	
Tensile Strength Max Load at 73.4°F (23°C):	lbs/in	30	80	150	MD	86
					CD	65
Elongation at Max Load 73.4°F (23°C):	%	2	4	3	MD	6
					CD	5
Ultimate Elongation 73.4°F (23°C):	%	3	40	2	MD	49
					CD	57
Tear Strength 73.4°F (23°C):	lbs	35	110	210	MD	95
					CD	82
Low Temperature Flexibility (As Mfg) :	maximum	-18°C (0°F)	-18°C (0°F)	-15°C (5°F)	MD & CD	-18°C (0°F)
Dimensional Stability:	% (max)	0.5	0.5	0.5	MD & CD	< 0.20
Compound Stability:	°C	102	102	91	102	

Ultimate Elongation is reported at point where load has dropped down to 5% of its original max.



188 S. Teilman Avenue • Fresno, California 93706-1334 U.S.A. • Toll Free: 800-621-9281 • Fax: 559-233-4607

www.mbtechnology.com

THE
DIFFERENCE
IS
QUALITY